

RESSALVA

Atendendo solicitação do(a)
autor(a), o texto completo desta
dissertação será disponibilizado
somente a partir
de 29/03/2020.



UNESP - Universidade Estadual Paulista
“Júlio de Mesquita Filho”
Faculdade de Odontologia de Araraquara



Victor Manuel Ochoa Rodríguez

**Physicochemical and biological properties of Biodentine associated with
radiopacifiers**

Araraquara

2018



UNESP - Universidade Estadual Paulista
Faculdade de Odontologia de Araraquara



Victor Manuel Ochoa Rodríguez

**Physicochemical and biological properties of Biodentine associated with
radiopacifiers**

Dissertação apresentada à Universidade Estadual Paulista (UNESP), Faculdade de Odontologia de Araraquara, para obtenção do grau de Mestre em Odontologia, na Área de Endodontia.

Orientador: Profa. Dra. Gisele Faria

Araraquara

2018

Ochoa Rodriguez, Victor Manuel

Physicochemical and biological properties of Biodentine associated
with radiopacifiers / Victor Manuel Ochoa Rodríguez. – Araraquara:
[s.n.], 2018

40 f.; 30 cm

Dissertação (Mestrado em Odontologia) – Universidade Estadual
Paulista, Faculdade de Odontologia

Orientadora: Profa. Dra. Gisele Faria

1. Dental cements 2. Endodontics 3. Materials testing I. Título

Victor Manuel Ochoa Rodríguez

Physicochemical and biological properties of Biodentine associated with radiopacifiers

Comissão julgadora

Dissertação para obtenção do grau de Mestre em Odontologia

Presidente e orientador: Gisele Faria

2º Examinador: Profa. Dra. Raquel Assed Bezerra Segato

3º Examinador: Prof. Dr. Mário Tanomaru-Filho

Araraquara, 29 de março de 2018.

CURRICULAR DATA

Victor Manuel Ochoa Rodríguez

BIRTH DATE: 23/11/1991 – Arequipa, Arequipa, Perú

AFFILIATE:

Victor Raúl Haya Ochoa Cuentas

Ana Maritza Trinidad Rodríguez Pérez

2009 - 2013

Graduated in Odontology.

Universidad Catolica de Santa Maria, U. SANTA MARIA, Arequipa-Peru

2016 - 2018

Specialist in Endodontics.

Araraquara School of Dentistry, São Paulo State University - UNESP, São Paulo, Brazil

2016-2018

Master in Dentistry.

Araraquara School of Dentistry, São Paulo State University - UNESP, São Paulo, Brazil

ACKNOWLEDGMENTS

To my advisor, Profa. Dra. Gisele Faria

Thanks for receiving me with open arms, showing me the way in difficult moments, for the effort you put in everything you do, for the time you give, regardless of how tired you are. I have been privileged to experience first-hand how critical and passionate you can be and make a big difference. You inspire me with your enthusiasm, support and confidence. You have set an example of excellence as a researcher, friend, mentor, instructor, and role model.

To Prof. Dr. Mario Tanomaru-Filho

I infinitely thank you for the opportunity given to me, for the guidance as professional, person and mentor. Thanks for the friendship and confidence. I am proud to have worked by your side.

To Prof. Hair Salas Beltrán

Thank you, my friend, for giving me the opportunity to learn from you. It was you and your encouragement to follow the endodontics path, that have brought me here.

To Dra. Elisandra Rodrigues

Thank you for the support, for the patience, the trust, confidence and friendship you have given me. Thanks for sharing all the smiles, laughs, and sometimes, the unhappy moments in the laboratory, you are an example and inspiration to me.

To the Teachers of the Discipline of Endodontics of this Faculty, **Prof. Dr. Fábio Luiz Camargo Vilella Berbert, Prof. Dr. Idomeo Bonetti-Filho, Profa. Dra. Juliane Maria Guerreiro-Tanomaru, Prof. Dr. Mário Tanomaru-Filho and Prof. Dr. Renato de Toledo Leonard.**

Thanks for the friendship, the happy moments, the laughs and stories shared. Thanks for the knowledge and wisdom you have left imprinted in me.

To my parents and little sister

Dr. Victor Ochoa Cuentas, Dra. Ana Rodríguez Pérez and Geraldine Ochoa Rodríguez who always supported me, encouraged and trusted me. Thank you for the good advices, the calls at night to ask about your patience, your life lessons, your trust and me. I still take your lessons with me, every day.

To the friends and colleagues of the Endodontic post grade

Thank you so much for the dedication, convivence, parties, laughs, advices, and good memories of each one. I thank you for the harmonious willingness to always help.

To the staff of the Technical Postgraduate Section, **José Alexandre Garcia and Cristiano Afonso Lamounier and the employees of the Department of Restorative Dentistry**

Thanks for the availability, efficiency, patience and joyfulness.

To the São Paulo State University "JÚLIO DE MESQUITA FILHO", UNESP, in UIC people of the Magnificent Rector Prof. Dr. **Sandro Roberto Valentini**

To the School of Dentistry at Araraquara (FOAr / UNESP), in the persons of the Director Profa. Dra. Elaine Maria Sgavioli Massucato.

**To the Postgraduate Program in Dentistry, FOAr / UNESP, in the people of the
Coordinator Prof. Dr. Joni Augusto Cirelli**

“Experience life in all possible ways; goodbad, bitter-sweet, dark-light, summer-winter. Experience all the dualities. Do not be afraid of experience, because the more experience you have, the more mature you become”

Rajneesh

Ochoa-Rodríguez VM. Propriedades físico-químicas e biológicas do Biodentine associado a radiopacificadores [dissertação de mestrado]. Araraquara: Faculdade de Odontologia da UNESP; 2018.

RESUMO

Biodentine™ (BD) apresenta bioatividade, biocompatibilidade e propriedades físico-químicas adequadas; no entanto, não possui radiopacidade adequada. Os objetivos foram avaliar (1) a radiopacidade de BD e BD associado com 15% de tungstato de cálcio (BDCaWO₄) ou óxido de zircônio (BDZrO₂), empregando sistemas de radiografia convencional e digital; e (2) as propriedades físico-químicas de tempo de presa, pH e solubilidade, e as propriedades biológicas de citocompatibilidade e potencial para induzir mineralização desses cimentos. Para a avaliação da radiopacidade, cada corpo de prova foi radiografado ao lado de uma escada de alumínio usando filme oclusal, placa de fósforo ou sensores digitais. As radiografias convencionais foram digitalizadas por câmera fotográfica ou scanner. Os valores médios de cinza dos materiais foram expressos em milímetros de alumínio (mm Al). A solubilidade foi avaliada após 7 dias de imersão dos espécimes em água destilada e expressa em porcentagem de perda de massa. O tempo de presa foi avaliado empregando a agulha de Gillmore (105 ± 0,5 g) e o pH foi mensurado com um medidor de pH. A citocompatibilidade e a bioatividade celular foram avaliadas em células de linhagem osteoblástica (Saos-2) utilizando os ensaios de metiltetrazólio (MTT), vermelho neutro (NR), atividade de fosfatase alcalina (ALP) e coloração de vermelho de alizarina. Os dados foram avaliados utilizando ANOVA de um fator e pós-teste Tukey ou ANOVA de dois fatores e pós-teste de Bonferroni ($\alpha=0,05$). A radiopacidade do BD foi inferior a 3 mm Al e do BDZrO₂ e BDCaWO₄ foi acima de 3 mm Al em todos os sistemas de radiografia utilizados. A solubilidade foi de 2,28% para BD, 2,27% para BDZrO₂ ($p>0,05$) e 3,63% para BDCaWO₄ ($p<0,05$). O tempo de presa foi de 27,5 min para BD, 33,5 minutos para BD ZrO₂ e 30 minutos para BDCaWO₄. Os ensaios MTT e NR revelaram que os extratos de cimentos, nas diluições 1: 2, 1: 4, 1: 8 e 1:12, apresentaram citocompatibilidade maior ($p<0,05$) ou similar ($p>0,05$) ao grupo controle (meio de cultura). A atividade de ALP nos grupos dos cimentos foi semelhante ($p>0,05$) ou maior ($p<0,05$) que o grupo controle aos 1, 3 e 7 dias. Aos 7 dias, a maior atividade de ALP foi detectada para o grupo BD seguido de BDZrO₂ ($p<0,05$) e do BDCaWO₄ ($p<0,05$). Não houve diferença significativa entre BDCaWO₄ e grupo controle ($p>0,05$). Todos os materiais induziram maior produção de nódulos mineralizados que grupo controle ($p<0,05$) sem diferença significativa entre eles. Em conclusão, a radiopacidade de BD foi inferior a 3 mm de Al em todos os sistemas radiográficos, e a adição de 15% de ZrO₂ ou CaWO₄ foi suficiente para aumentar a radiopacidade de BD para valores maiores que o mínimo recomendado pelo ISO 6876 (>3mm Al). BD associado a radiopacificadores mostrou propriedades adequadas do tempo de presa, pH e solubilidade, exceto BDCaWO₄, que apresentou maior solubilidade que BD e BDZrO₂. Todos os cimentos apresentaram citocompatibilidade e potencial de induzir mineralização em células Saos-2. Os resultados sugerem que a adição de 15% de ZrO₂ pode ser uma boa opção para aumentar a radiopacidade do BD sem alterar suas propriedades físico-químicas e biológicas.

Palavras-chave: Cimentos dentários. Endodontia. Teste de materiais.

Ochoa-Rodríguez VM. Physicochemical and biological properties of Biodentine associated with radiopacifiers [dissertação de mestrado]. Araraquara: Faculdade de Odontologia da UNESP; 2018.

ABSTRACT

Biodentine™ (BD) presents bioactivity, biocompatibility and suitable physicochemical properties; however, it does not have adequate radiopacity. The objectives were to evaluate (1) the radiopacity of BD and BD associated with 15% calcium tungstate (BDCaWO₄) or zirconium oxide (BDZrO₂), employing conventional and digital radiography systems; and (2) the physicochemical properties of setting time, pH and solubility, and biological properties of cytocompatibility and potential to induce mineralization of these cements. For radiopacity evaluation, each cement specimen was radiographed alongside an aluminum step-wedge using occlusal film, photostimulable phosphor plates or digital sensors. The conventional radiographies were digitized by digital photographic camera or scanner. Mean grey values of materials were expressed in millimeters of aluminum (mm Al). Solubility was evaluated after 7 days of specimens' immersion in distilled water and expressed as percentage of mass loss. Setting time was evaluated employing a Gillmore needle (105 ± 0.5 g) and pH was evaluated with pH meter. The cytocompatibility and cell bioactivity were evaluated in osteoblasts-like cells (Saos-2) using methyl-thiazol-tetrazolium (MTT), neutral red (NR), alkaline phosphatase (ALP) activity and alizarin red staining assays. The data were evaluated using one-way ANOVA and Tukey post-test or two-way ANOVA and Bonferroni post-test ($\alpha=0.05$). BD radiopacity was below 3 mm Al and BDZrO₂ and BDCaWO₄ was above 3 mm Al in all radiography systems used. Solubility was 2.28% for BD, 2.27% for BDZrO₂ ($p>0.05$) and 3.63% for BDCaWO₄ ($p<0.05$). All cements showed alkaline pH with no statistical difference between them ($p>0.05$). The setting time was 27.5 min. for BD, 33.5 min. for BDZrO₂ and 30 min. for BDCaWO₄. MTT and NR assays revealed that cements extract at dilutions of 1:2, 1:4, 1:8 and 1:12 had greater ($p<0.05$) or similar ($p>0.05$) cytocompatibility in comparison to control group (culture medium). The ALP activity of cements groups at 1, 3 and 7 days was similar ($p>0.05$) or greater ($p<0.05$) than the control group. At 7 days, the highest ALP activity was detected for BD group followed by BDZrO₂ ($p<0.05$) and BDCaWO₄ group ($p<0.05$). There was no significant difference between BDCaWO₄ and control group ($p>0.05$). All materials induced greater production of mineralized nodules than control group ($p<0.05$) without significant difference among them. In conclusion, BD radiopacity was below 3 mm Al in all radiography systems, and addition of 15% ZrO₂ or CaWO₄ was sufficient to increase the radiopacity of BD to values greater than the minimum recommended by ISO 6876 (> 3 mm Al). BD associated with radiopacifiers showed suitable properties of setting time, pH and solubility, except BDCaWO₄, which exhibit a higher solubility than BD and BDZrO₂. All cements had cytocompatibility and potential to induce mineralization in Saos-2 cells. The results suggest that the addition of 15% ZrO₂ may be a good option to increase the radiopacity of BD without altering its physicochemical and biological properties.

Key words: Dental cements. Endodontics. Materials testing.

SUMMARY

1 INTRODUCTION	11
2 OBJETIVES.....	15
3 MATERIAL AND METHODS	16
4 RESULTS	22
5 DISCUSSION.....	28
6 CONCLUSIONS.....	31
REFERENCES	32

1 INTRODUCTION

MTA is mainly composed of Portland cement (PC) and contains 53.1% of tricalcium silicate, 22.5% of dicalcium silicate, 21.6% of bismuth oxide (Bi_2O_3) as radiopacifier and traces of calcium sulfate (Torabinejad, White⁸⁷, 1998; Camilleri et al.¹⁶, 2005; Camilleri²⁰, 2007; Camilleri¹⁹, 2008). It is considered the gold standard material for diverse treatments in endodontics, such as root perforation, root-end filling, among others (Hwang et al.⁴⁶, 2011; Torabinejad et al.⁸⁸, 2018), due to its sealing capability, biocompatibility and ability to induce mineralization (Parirokh, Torabinejad⁶⁶, 2010; Tanomaru-Filho et al.⁸³, 2017; Rodrigues et al.⁷³, 2017). However, MTA is difficult to manipulate and insert into cavities (Parirokh, Torabinejad⁶⁶, 2010), low compressive strength (Parirokh, Torabinejad⁶⁵, 2010), has a long setting time (Parirokh, Torabinejad⁶⁵, 2010; Tanomaru-Filho et al.⁸⁶, 2012) and causes tooth discoloration (Belobrov, Parashos⁸, 2011; Akbari et al.¹, 2012; Felman, Parashos³², 2013; Kang et al.⁵¹, 2015) derived from the chemical reaction between the collagen in the dentin matrix and Bi_2O_3 (Marciano et al.⁵⁹, 2014). There is evidence that Bi_2O_3 causes structural damages capable of compromising the longevity of the material, increasing the porosity degree, and consequently reducing the compressive strength (Coomaraswamy et al.²⁷, 2007).

Tricalcium silicate, the principal active component in MTA (Camilleri¹⁶, 2005), has been used with or without additives as bone cement (Huan, Chang⁴², 2008; Zhao et al.⁹⁷, 2008), posterior restorative material (Laurent et al.⁵⁶, 2008) and reparative dental material (Wang et al.⁹³, 2008; Camilleri et al.¹⁷, 2013). It has shown suitable physicochemical properties (Wang et al.⁹³, 2008; Huan, Chang⁴², 2008), bioactivity and biocompatibility (Peng et al.⁶⁹, 2011; Camilleri et al.¹⁷, 2013; Tanomaru-Filho et al.⁸³, 2017), besides promoting odontoblastic differentiation of human dental pulp cells (Peng et al.⁶⁹, 2011). The hydration of the tricalcium silicate after chemical reaction with tissue fluids forms hydrated calcium silicate gel and calcium hydroxide, thus, being the tricalcium silicate phase responsible for the bioactivity of this material (Camilleri¹⁸, 2011; Khalil et al.⁵⁴, 2016). Dental materials based on tricalcium silicate have been developed. These materials are synthesized in the laboratory from high purity raw materials unlike the Portland cement in MTA. One such formulation is BiodentineTM – BD (Septodont, Saint-Maurdes-Fossés, France) which was developed for use as a bioactive dentin substitute and has been indicated for coronal and radicular restorations, pulp capping, pulpotomy, root and furcation perforations, apexification, root resorption and as root-end filling (Rajasekharan et al.⁷⁰, 2014). BD is composed of a powder and liquid system. The powder contains 80% tricalcium silicate (main component), 15% calcium carbonate

(filler material), 5% zirconium oxide (radiopacifier), dicalcium silicate (traces), calcium oxide (traces), iron oxide (traces). The mixing liquid is an aqueous solution of a hydrosoluble polymer (water reducing agent) with calcium chloride, which decreases the setting time of the cement (Septodont)⁷⁶. Studies show that this cement has biocompatibility (Fonseca et al.³³, 2016), bioactivity (Grech et al.³⁹, 2013), with better handling conditions (Butt et al.¹³, 2014) and lower setting time in relation to MTA (Kaup et al.⁵³, 2015).

The biological properties of BD have been studied, showing positive responses. BD presents cytocompatibility (Chang et al.²⁴, 2014; Daltoe et al.³⁰, 2016; Rodrigues et al.⁷⁴, 2017) and in vitro potential to induce mineralization (Gomes- Cornélio et al.³⁷, 2017) higher than MTA (Collado-González et al.²⁵, 2017; Rodrigues et al.⁷⁴, 2017). In vivo, BD promotes formation of collagenous capsules when implanted in the subcutaneous tissue of rats (Fonseca et al.³³, 2016) and induces the formation of mineralized tissue when used as pulp-capping material in human and dog teeth (Nowicka et al.⁶³, 2013; De Rossi et al.³¹, 2014; Cuadros-Fernández et al.²⁸, 2016) or when used for the sealing of furcation perforations (Silva et al.⁸⁰, 2017).

The physicochemical properties of BD have benefit in relation to MTA. The initial setting time ranges from 9 minutes (Septodont)⁷⁶ to 16 minutes (Lucas et al.⁵⁸, 2017) and the final setting time from 35 minutes (Lucas et al.⁵⁸, 2017) to 85.6 minutes (Kaup et al.⁵³, 2015), which is lower than MTA (Parirokh et al.⁶⁷, 2018). The polycarboxylate-based hydrosoluble polymers in the liquid of BD acts as water reducing agent and allows low water/powder ratio. As a result, BD has lower porosity and, consequently, higher compressive strength than MTA (Camilleri et al.¹⁷, 2013; Lucas et al.⁵⁸, 2017). BD presents alkaline pH similar to MTA (Lucas et al.⁵⁸, 2017). This pH is derived from the hydration reaction of tricalcium silicate which forms calcium hydroxide and calcium silicate hydrate gel (Camilleri et al.¹⁷, 2013; Khalil et al.⁵⁴, 2016).

Despite of the good properties, some in vitro studies, using conventional film (Lucas et al.⁵⁸, 2017) or photostimulable phosphor plates (Tanalp et al.⁸², 2013), have shown that BD presents lower radiopacity than that recommended by the International Standards Organization (ISO 6876)⁴⁸. According to ISO standard, the endodontic sealers must have a radiopacity equivalent to not less than 3 mm Al (ISO 6876)⁴⁸. Moreover, researchers, who have used BD as a retrograde obturation material in human teeth, have reported that low radiopacity is the primary clinical limitation of BD, which makes radiographic assessment of treatment and follow-up difficult (Bachoo et al.⁵, 2013; Caron et al.²², 2014). Considering the appropriate properties of tricalcium silicate-based cements associated with zirconium oxide

(ZrO₂) and calcium tungstate - CaWO₄ (Cutajar et al.²⁹, 2011; Gomes-Cornélio et al.³⁸, 2011; Húngaro Duarte et al.⁴⁴, 2012; Camilleri et al.¹⁷, 2013; Bosso-Martelo et al.¹¹, 2015; Silva et al.⁷⁹, 2017), an option to improve BD's radiopacity is to associate it with these radiopacifiers.

CaWO₄ has been used as an alternative radiopacifier to Bi₂O₃ for calcium silicate-based cements (Marciano et al.⁶⁰, 2016). Studies have reported that CaWO₄ associated with Portland cement, promotes alkaline pH (Húngaro-Duarte et al.⁴⁴, (2012), decreases the solubility, increases the compressive strength, does not affect the final setting time (Tanomaru-Filho et al.⁸⁶, 2012) and is not cytotoxic for periodontal and osteoblast-like cells (Gomes-Cornélio et al.³⁸, 2011). CaWO₄, associated with calcium silicate-based cement, presents bioactivity (Bosso-Martelo et al.¹¹, 2015) and maintains physicochemical properties similar to MTA (Bosso-Martelo et al.¹², 2016).

ZrO₂ was initially introduced as a biomaterial for use in joint implants in orthopedic surgery. In restorative dentistry, ZrO₂ is used to replace the metal framework in crown and bridges and as radiopacifier in glass ionomer cements (McCabe et al.⁶¹, 2003). It is commonly used in combination with tricalcium silicate cements for endodontic use (Viapiana et al.⁹¹, 2014; Tanomaru et al.⁸⁵, 2017) including BD. ZrO₂ does not participate in the hydration process of Portland cement thus being inert when compared to Bi₂O₃ (Camilleri et al.¹⁴, 2011; Camilleri et al.¹⁷, 2013). The association of Portland cement with 30% ZrO₂ resulted in a material with physicochemical properties comparable to those of MTA (Cutajar et al.²⁹, 2011). ZrO₂ in association with white Portland cement induced lower inflammatory reaction than Bi₂O₃ (Silva et al.⁷⁸, 2014), fibroblast proliferation and accelerated the regression of the inflammatory reaction when compared to MTA (Silva et al.⁷⁹, 2017) in subcutaneous rat tissue.

Radiopacity of endodontic materials should be sufficient to allow distinction from dentin or cortical bone (American National Standard/American Dental Association - ANSI/ADA)³. For quantifying the radiopacity of endodontic materials, specimens should be prepared in standard discs and radiographed along with an aluminum (Al) step-wedge reference with at least 98% pure, using type D or E occlusal films (ISO 6876)⁴⁸. Values in terms of Al equivalent thickness minimize the influence of exposure time and film development time (Rasimick et al.⁷¹, 2007; Akcay et al.², 2012). ISO standard recommend that radiopacity must be evaluated in conventional radiographic films using an optical densitometer (ISO 6876)⁴⁸. However, nowadays, the radiopacity of dental materials has been performed using digital images obtained by indirect (Akcay et al.², 2012; Siboni et al.⁷⁷, 2017) or direct technique (Baksi et al.⁶, 2007; Akcay et al.², 2012; Khalil et al.⁵⁴, 2016, Versiani et

al.⁹⁰, 2016). In the indirect technique, the conventional radiographic image is converted into digital sign using radiographic scanner (Tanomaru-Filho et al.⁸⁴, 2007; Akcay et al.², 2012; Siboni et al.⁷⁷, 2017) or digital photographic camera (Húngaro Duarte et al.⁴³, 2009; Candeiro et al.²¹, 2012; Wang et al.⁹⁴, 2014). In the direct technique, digital radiography is obtained using digital sensors or photostimulable phosphor plates (Baksi et al.⁷, 2008; Akcay et al.², 2012; Grech et al.⁴⁰, 2013; Khalil et al.⁵⁴, 2016, Versiani et al.⁹⁰, 2016).

Although several studies have assessed the radiopacity of endodontic materials by using digital systems (Rasimick et al.⁷¹, 2007; Baksi et al.⁷, 2008; Akcay et al.², 2012; Grech et al.⁴⁰, 2013, Camilleri et al.¹⁷, 2013; Khalil et al.⁵⁴, 2016, Versiani et al.⁹⁰, 2016), there is no consensus on how digital radiography influences the radiopacity of materials. Rasimick et al.⁷¹ (2007) reported that barium-containing materials tended to be 13% more radiopaque in radiographs obtained by digital sensor than on the conventional film type. On the other hand, other endodontic materials appeared less radiopaque on digital radiography, ranging from 7% to 20% difference between conventional and digital radiography obtained by photostimulable phosphor plates (Baksi et al.⁷, 2008). Therefore, it is important to evaluate the radiopacity of BD and BD associated with radiopacifiers using conventional and digital radiography systems. In addition, it is important to evaluate the effect of the addition of the radiopacifiers on the physicochemical and biological properties of BD.

6 CONCLUSIONS

BD radiopacity was lower than 3 mm Al in the conventional and digital radiography systems, and addition of 15% ZrO_2 or CaWO_4 was sufficient to increase the radiopacity of BD to values greater than the minimum recommended by ISO 6876 (> 3 mm Al). BD associated with radiopacifiers showed suitable properties of setting time, pH and solubility, except BD CaWO_4 , which exhibit higher solubility than BD and BDZrO_2 . All cements evaluated had citocompatibility and potential to induce mineralization in Saos-2 cells. The results suggest that the addition of 15% ZrO_2 may be a good option to increase the radiopacity of BD, allowing its radiograph detection in clinical practice, without altering its physicochemical and biological properties.

REFERENCES*

1. Akbari M, Rouhani A, Samiee S, Jafarzadeh H. Effect of dentin bonding agent on the prevention of tooth discoloration produced by mineral trioxide aggregate. *Int J Dent.* 2012; 2012:563203
2. Akcay I, Ilhan B, Dundar N. Comparison of conventional and digital radiography systems with regard to radiopacity of root canal filling materials. *Int Endod J.* 2012; 45(8):730-6.
3. American National Standard/American Dental Association (ANSI/ADA). Specification n.57: endodontic sealing material. Chicago: ANSI/ADA; 2000
4. Andolfatto C, Bonetti-Filho I, Carlos IZ, Guerreiro-Tanomaru JM, Kuga MC, Tormin FBC, et al. Cytocompatibility, physical properties, and antibiofilm activity of endodontic sealers with amoxicillin. *Microsc Res Tech.* 2017; 80(9):1036-48.
5. Bachoo IK, Seymour D, Brunton P. Clinical case reports using a novel calcium-based cement. *Br Dent J.* 2013; 214(2):61-4.
6. Baksi BG, Ermis RB. Comparison of conventional and digital radiography for radiometric differentiation of dental cements. *Quintessence Int.* 2007; 38(9): 532-6.
7. Baksi BG, Sen BH, Eyuboglu TF. Differences in aluminum equivalent values of endodontic sealers: conventional versus digital radiography. *J Endod.* 2008; 34(9):1101-4.
8. Belobrov I, Parashos P. Treatment of tooth discoloration after the use of white mineral trioxide aggregate. *J Endod.* 2011; 37(7):1017-20
9. Bortoluzzi EA, Broon NJ, Bramante CM, Felipe WT, Tanomaru Filho M, Esberard RM. The influence of calcium chloride on the setting time, solubility, disintegration, and pH of mineral trioxide aggregate and white Portland cement with a radiopacifier. *J Endod.* 2009; 35(4):550-4.
10. Bortoluzzi EA, Guerreiro-Tanomaru JM, Tanomaru-Filho M, Duarte MA. Radiographic effect of different radiopacifiers on a potential retrograde filling material. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod.* 2009; 108(4):628–32.

* De acordo com o Guia de Trabalhos Acadêmicos da FOAr, adaptado das Normas Vancouver. Disponível no site da Biblioteca: <http://www.foar.unesp.br/Home/Biblioteca/guia-de-normalizacao-atualizado.pdf>

11. Bosso-Martelo R, Guerreiro-Tanomaru JM, Viapiana R, Berbert FL, Basso Bernardi MI, Tanomaru-Filho M. Calcium silicate-based cements associated with micro- and nanoparticle radiopacifiers: physicochemical properties and bioactivity. *Int Sch Res Notices*. 2015; 2015:874283.
12. Bosso-Martelo R, Guerreiro-Tanomaru JM, Viapiana R, Berbert FLC, Húngaro-Duarte MA, Tanomaru-Filho M. Physicochemical properties of calcium silicate cements associated with microparticulate and nanoparticulate radiopacifiers. *Clin Oral Investig*. 2016; 20(1):83-90.
13. Butt N, Talwar S, Chaudhry S, Nawal RR, Yadav S, Bali A. Comparison of physical and mechanical properties of mineral trioxide aggregate and Biodentine. *Indian J Dent Res*. 2014; 25(6):692-7.
14. Camilleri J, Cutajar A, Mallia B. Hydration characteristics of zirconium oxide replaced Portland cement for use as a root-end filling material. *Dent Mater*. 2011; 27(8):845–54
15. Camilleri J, Gandolfi MG. Evaluation of the radiopacity of calcium silicate cements containing different radiopacifiers. *Int Endod J*. 2010; 43(1):21–30.
16. Camilleri J, Montesin FE, Brady K, Sweeney R, Curtis RV, Ford TR. The constitution of mineral trioxide aggregate. *Dent Mater*. 2005; 21(4):297-303.
17. Camilleri J, Sorrentino F, Damidot D. Investigation of the hydration and bioactivity of radiopacified tricalcium silicate cement, Biodentine and MTA Angelus. *Dent Mater*. 2013; 29(5):580-93.
18. Camilleri J. Characterization and hydration kinetics of tricalcium silicate cement for use as a dental biomaterial. *Dent Mater*. 2011; 27(8):836–44.
19. Camilleri J. Characterization of hydration products of mineral trioxide aggregate. *Int Endod J*. 2008; 41(5):408-17.
20. Camilleri J. Hydration mechanisms of mineral trioxide aggregate. *Int Endod J*. 2007; 40(6):462-70.
21. Candeiro GT, Correia FC, Duarte MA, Ribeiro-Siqueira DC, Gavini G. Evaluation of radiopacity, pH, release of calcium ions, and flow of a bioceramic root canal sealer. *J Endod*. 2012; 38(6):842-5.
22. Caron G, Azérad J, Faure MO, Machtou P, Boucher Y. Use of a new retrograde filling material (Biodentine) for endodontic surgery: two case reports. *Int J Oral Sci*. 2014; 6(4):250-3.
23. Carvalho-Junior JR, Correr-Sobrinho L, Correr AB, Sinhoreti MA, Consani S, Sousa-Neto MD. Solubility and dimensional change after setting of root canal sealers: a proposal for smaller dimensions of test samples. *J Endod*. 2007; 33(9):1110-6.

24. Chang SW, Lee SY, Ann HJ, Kum KY, Kim EC. Effects of calcium silicate endodontic cements on biocompatibility and mineralization-inducing potentials in human dental pulp cells. *J Endod.* 2014; 40(8):1194-200.
25. Collado-González M, García-Bernal D, Oñate-Sánchez RE, Ortolani-Seltenerich PS, Álvarez-Muro T, Lozano A, et al. Cytotoxicity and bioactivity of various pulpotomy materials on stem cells from human exfoliated primary teeth. *Int Endod J.* 2017; 50 Suppl 2:19-30.
26. Collares FM, Klein M, Santos PD, Portella FF, Ogliari F, Leitune VC, et al. Influence of radiopaque fillers on physicochemical properties of a model epoxy resin-based root canal sealer. *J Appl Oral Sci.* 2013; 21(6):533-9.
27. Coomaraswamy KS, LumLey PJ, Hofmann MP. Effect of bismuth oxide radiopacifier content on the material properties of an endodontic Portland cement-based (MTAlike) system. *J Endod.* 2007;33(3): 295–8.
28. Cuadros-Fernández C, Lorente Rodríguez AI, Sáez-Martínez S, García-Binimelis J, About I, Mercadé M. Short-term treatment outcome of pulpotomies in primary molars using mineral trioxide aggregate and Biodentine: a randomized clinical trial. *Clin Oral Investig.* 2016; 20(7):1639-45.
29. Cutajar A, Mallia B, Abela S, Camilleri J. Replacement of radiopacifier in mineral trioxide aggregate; characterization and determination of physical properties. *Dent Mater.* 2011; 27(9):879-91.
30. Daltoé MO, Paula-Silva FW, Faccioli LH, Gatón-Hernández PM, De Rossi A, Bezerra Silva LA. Expression of mineralization markers during pulp response to Biodentine and Mineral Trioxide Aggregate. *J Endod.* 2016; 42(4):596-603.
31. De Rossi A, Silva LA, Gatón-Hernández P, Sousa-Neto MD, Nelson-Filho P, Silva RA, et al. Comparison of pulpal responses to pulpotomy and pulp capping with biodentine and mineral trioxide aggregate in dogs. *J Endod.* 2014; 40(9):1362-9.
32. Felman D, Parashos P. Coronal tooth discoloration and white mineral trioxide aggregate. *J Endod.* 2013; 39(4):484–7.
33. Fonseca TS, da Silva GF, Tanomaru-Filho M, Sasso-Cerri E, Guerreiro-Tanomaru JM, Cerri PS. In vivo evaluation of the inflammatory response and IL-6 immunoexpression promoted by Biodentine and MTA Angelus. *Int Endod J.* 2016; 49(2):145-53.
34. Gandolfi MG, Siboni F, Prati C. Properties of a novel polysiloxane-guttapercha calcium silicate-bioglass-containing root canal sealer. *Dent Mat.* 2016; 32(5):113-26.
35. Gandolfi MG, Taddei P, Modena E, Siboni F, Prati C. Biointeractivity-related versus chemi/physisorption-related apatite precursor-forming ability of current root end filling materials. *J Biomed Mater Res B Appl Biomater.* 2013; 101(7):1107-23

36. Golub E, Boesze-Battaglia K. The role of alkaline phosphatase in mineralization. *Curr Opin Orthop*. 2007; 18(5):444-8.
37. Gomes-Cornélio AL, Rodrigues EM, Salles LP, Mestieri LB, Faria G, Guerreiro-Tanomaru JM, et al. Bioactivity of MTA Plus, Biodentine and an experimental calcium silicate-based cement on human osteoblast-like cells. *Int Endod J*. 2017; 50(1):39-47.
38. Gomes Cornélio AL, Salles LP, Campos da Paz M, Cirelli JA, Guerreiro-Tanomaru JM, Tanomaru Filho M. Cytotoxicity of Portland cement with diferente radiopacifying agents: a cell death study. *J Endod*. 2011; 37(2):203-10.
39. Grech L, Mallia B, Camilleri J. Characterization of set intermediate restorative material, Biodentine, Bioaggregate and a prototype calcium silicate cement for use as root-end filling materials. *Int Endod J*. 2013; 46(7):632-41.
40. Grech L, Mallia B, Camilleri J. Investigation of the physical properties of tricalcium silicate cement-based root-end filling materials. *Dent Mater*. 2013; 29(2):20-8.
41. Guerreiro-Tanomaru JM, Cornélio AL, Andolfatto C, Salles LP, Tanomaru-Filho M. pH and antimicrobial activity of Portland cement associated with different radiopacifying agents. *ISRN Dent*. 2012; 2012:469019
42. Huan Z, Chang J. Study on physicochemical properties and in vitro bioactivity of tricalcium silicate- calcium carbonate composite bone cement. *J Mater Sci Mater Med*. 2008; 19(8):2913-8.
43. Húngaro Duarte MA, de Oliveira El Kadre GD, Vivian RR, Guerreiro Tanomaru JM, Tanomaru Filho M, de Moraes IG. Radiopacity of Portland cement associated with different radiopacifying agents. *J Endod*. 2009; 35(5):737-40.
44. Hungaro Duarte MA, Minotti PG, Rodrigues CT, Zapata RO, Bramante CM, Tanomaru Filho M, et al. Effect of diferente radiopacifying agentes on the physicochemical properties of white Portland cement and white mineral trioxide aggregate. *J Endod*. 2012; 38(3):394-7.
45. Hungaro Duarte MA, Tanomaru Filho M, Gomes de Moraes I. Evaluation of the physical and chemical properties of two commercial and three experimental root-end filling materials. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod*. 2010; 110(2):250-6.
46. Hwang YC, Kim DH, Hwang IN, Song SJ, Park YJ, Koh JT, Son HH, Oh WM. Chemical constitution, physical properties, and biocompatibility of experimentally manufactured Portland cement. *J Endod*. 2011, 37(1):58-62.

47. International Organization for Standardization. ISO 10993-5: biological evaluation of medical devices - Part 5. Tests for in vitro cytotoxicity. London, UK: British Standards Institution; 2009.
48. International Organization for Standardization. ISO 6876: dentistry: root canal sealing materials. London, UK: British Standards Institution; 2012.
49. Ioannidis K, Mistakidis I, Beltes P, Karagiannis V. Spectrophotometric analysis of coronal discoloration induced by grey and white MTA. *Int Endod J.* 2013; 46(2):137-44.
50. Jung JY, Woo SM, Lee BN, Koh JT, Nör JE, Hwang YC. Effect of Biodentine and Bioaggregate on odontoblastic differentiation via mitogen-activated protein kinase pathway in human dental pulp cells. *Int Endod J.* 2015; 48(2):177-84.
51. Kang SH, Shin YS, Lee HS, Kim SO, Shin Y, Jung IY, Song JS. Color changes of teeth after treatment with various mineral trioxide aggregate-based materials: an ex vivo study. *J Endod.* 2015; 41(5):737-41.
52. Katara G, Hemvani N, Chitnis S, Chitnis V, Chitnis DS. Surface disinfection by exposure to germicidal UV light. *Indian J Med Microbiol.* 2008; 26(3):241-2.
53. Kaup M, Schäfer E, Dammaschke T. An in vitro study of different material properties of Biodentine compared to ProRoot MTA. *Head Face Med.* 2015; 2:11-6.
54. Khalil I, Alfred Naaman, DDS, Josette Camilleri. Properties of tricalcium silicate sealers. *J Endod.* 2016; 42(10):1529-35.
55. Khan SIR, Ramachandran A, Deepalakshmi M, Kumar KS. Evaluation of pH and calcium ion release of mineral trioxide aggregate and a new root-end filling material. *E-Journal of Dentistry.* 2012; 2(2):166-9.
56. Laurent P, Camps J, De Méo M, Déjou J, About I. Induction of specific cell responses to a Ca_3SiO_5 -based posterior restorative material. *Dent Mater.* 2008; 24(11):1486-94.
57. Li Q, Deacon AD, Coleman NJ. The impact of zirconium oxide nanoparticles on the hydration chemistry and biocompatibility of white Portland cement. *Dent Mater J.* 2013; 32(5):808-15
58. Lucas CP, Viapiana R, Bosso-Martelo R, Guerreiro-Tanomaru JM, Camilleri J, Tanomaru-Filho M. Physicochemical properties and dentin bond strength of a Tricalcium Silicate-Based retrograde material. *Braz Dent J.* 2017; 28(1):51-6.
59. Marciano MA, Costa RM, Camilleri J, Mondelli RF, Guimarães BM, Duarte MA. Assessment of color stability of white mineral trioxide aggregate angelus and bismuth oxide in contact with tooth structure. *J Endod.* 2014; 40(8):1235-40.

60. Marciano MA, Duarte MA, Camilleri J. Calcium silicate-based sealers: assessment of physicochemical properties, porosity and hydration. *Dent Mater.* 2016; 32(2): e30-40.
61. McCabe JF, Walls AWF. *Applied dental materials.* 9th ed. Oxford: Blackwell; 2008.
62. Margunato S, Taşlı PN, Aydın S, Karapınar Kazandağ M, Şahin F. In vitro evaluation of ProRoot MTA, Biodentine, and MM-MTA on human alveolar bone marrow stem cells in terms of biocompatibility and mineralization. *J Endod.* 2015; 41(10):1646-52.
63. Nowicka A, Lipski M, Parafiniuk M, Sporniak-Tutak K, Lichota D, Kosierkiewicz A, et al. Response of human dental pulp capped with biodentine and mineral trioxide aggregate. *J Endod* 2013; 39(6):743-7.
64. Okabe T, Sakamoto M, Takeuchi H, Matsushima K. Effects of pH on mineralization ability of human dental pulp cells. *J Endod.* 2006; 32(3):198-201.
65. Parirokh M, Torabinejad M. Mineral trioxide aggregate: a comprehensive literature review--Part I: chemical, physical, and antibacterial properties. *J Endod.* 2010; 36(1):16-27.
66. Parirokh M, Torabinejad M. Mineral trioxide aggregate: a comprehensive literature review--Part III: Clinical applications, drawbacks, and mechanism of action. *J Endod.* 2010; 36(3):400-13.
67. Parirokh M, Torabinejad M, Dummer PMH. Mineral trioxide aggregate and other bioactive endodontic cements: an updated overview - part I: vital pulp therapy. *Int Endod J.* 2018; 51(2):177-205.
68. Paul H, Reginato AJ, Schumacher HR. Alizarin red S staining as a screening test to detect calcium compounds in synovial fluid. *Arthritis Rheum.* 1983; 26(2):191-200.
69. Peng W, Liu W, Zhai W, Jiang L, Li L, Chang J, et al. Effect of tricalcium silicate on the proliferation and odontogenic differentiation of human dental pulp cells. *J Endod.* 2011; 37(9):1240-6.
70. Rajasekharan S, Martens LC, Cauwels RG, Verbeeck RM. Biodentine™ material characteristics and clinical applications: a review of the literature. *Eur Arch Paediatr Dent.* 2014; 15(3):147-58.
71. Rasimick BJ, Shah RP, Musikant BL, Deutsch AS. Radiopacity of endodontic materials on film and a digital sensor. *J Endod.* 2007; 33(9):1098-101.
72. Repetto G, del Peso A, Zurita JL. Neutral red uptake assay for the estimation of cell viability/cytotoxicity. *Nat Protoc.* 2008; 3(7):1125-31.

73. Rodrigues EM, Gomes -Cornélio AL, Mestieri LB, Fuentes ASC, Salles LP, Rossa-Junior C, et al. Human dental pulp cells response to mineral trioxide aggregate (MTA) and MTA Plus: cytotoxicity and gene expression analysis. *Int Endod J.* 2017; 50(8):780-9.
74. Rodrigues EM, Gomes-Cornélio AL, Soares-Costa A, Salles LP, Velayutham M, Rossa-Junior C, et al. An assessment of the overexpression of BMP-2 in transfected human osteoblast cells stimulated by mineral trioxide aggregate and Biodentine. *Int Endod J.* 2017; 50 Suppl 2:9-18.
75. Scelza MZ, Linhares AB, da Silva LE, Granjeiro JM, Alves GG. A multiparametric assay to compare the cytotoxicity of endodontic sealers with primary human osteoblasts. *Int Endod J.* 2012; 45(1):12-8.
76. Septodont's Research Group. Biodentine™: Active Biosilicate Technology™: scientific file. Saint-Maur-des-Fossés Cedex: R&D; 2010.
77. Siboni F, Taddei P, Prati C, Gandolfi MG. Properties of Neo MTA Plus and MTA Plus cements for endodontics. *Int Endod J.* 2017; 50 Suppl 2:83-94.
78. Silva GF, Bosso R, Ferino RV, Tanomaru-Filho M, Bernardi MI, Guerreiro-Tanomaru JM, et al. Microparticulated and nanoparticulated zirconium oxide added to calcium silicate cement: Evaluation of physicochemical and biological properties. *J Biomed Mater Res A.* 2014; 102(12):4336-45.
79. Silva GF, Guerreiro-Tanomaru JM, da Fonseca TS, Bernardi MIB, Sasso-Cerri E, Tanomaru-Filho M, et al. Zirconium oxide and niobium oxide used as radiopacifiers in a calcium silicate-based material stimulate fibroblast proliferation and collagen formation. *Int Endod J.* 2017; 50 Suppl 2: e95-e108
80. Silva LAB, Pieroni KAMG, Nelson-Filho P, Silva RAB, Hernández-Gatón P, Lucisano MP, et al. Furcation perforation: periradicular tissue response to Biodentine as a repair material by histopathologic and indirect immunofluorescence analyses. *J Endod.* 2017; 43(7):1137-42.
81. Singh S, Podar R, Dadu S, Kulkarni G, Purba R. Solubility of a new calcium silicate-based root-end filling material. *J Conserv Dent.* 2015; 18(2):149-53.
82. Tanalp J, Karapınar-Kazandağ M, Dölekoğlu S, Kayahan MB. Comparison of the radiopacities of different root-end filling and repair materials. *ScientificWorldJournal.* 2013; 2013:594950.
83. Tanomaru-Filho M, Andrade AS, Rodrigues EM, Viola KS, Faria G, Camilleri J, et al. Biocompatibility and mineralized nodule formation of Neo MTA Plus and an

- experimental tricalcium silicate cement containing tantalum oxide. *Int Endod J.* 2017; 50 Suppl 2:31-9.
84. Tanomaru-Filho M, Jorge EG, Guerreiro Tanomaru JM, Gonçalves M. Radiopacity evaluation of new root canal filling materials by digitalization of images. *J Endod.* 2007;33(3):249-51.
85. Tanomaru-Filho M, Torres FFE, Chávez-Andrade GM, de Almeida M, Navarro LG, Steier L, et al. Physicochemical properties and volumetric change of silicone/bioactive glass and calcium silicate-based endodontic sealers. *J Endod.* 2017; 43(12):2097-101
86. Tanomaru-Filho M, Morales V, da Silva GF, Bosso R, Reis JM, Húngaro-Duarte MA, et al. Compressive strength and setting time of MTA and Portland cement associated with different radiopacifying agents. *ISRN Dent.* 2012; 2012:898051.
87. Torabinejad M, White DJ inventors; Loma Linda University, assignee. Tooth filling material and method of use. United States patent 5769638.1998 Jun 23.
88. Torabinejad M, Parirokh M, Dummer PMH. Mineral trioxide aggregate and other bioactive endodontic cements: an updated overview - part II: other clinical applications and complications. *Int Endod J.* 2018; 51(3):284-317.
89. Torres FFE, Bosso-Martelo R, Espir CG, Cirelli JA, Guerreiro-Tanomaru JM, Tanomaru-Filho M. Evaluation of physicochemical properties of root-end filling materials using conventional and Micro-CT tests. *J Appl Oral Sci.* 2017; 25(4):374-80.
90. Versiani MA, Abi Rached-Junior FJ, Kishen A, Pécora JD, Silva-Sousa YT, de Sousa-Neto MD. Zinc oxide nanoparticles enhance physicochemical characteristics of Grossman Sealer. *J Endod.* 2016; 42(12):1804-10.
91. Viapiana R, Flumignan DL, Guerreiro-Tanomaru JM, Camilleri J, Tanomaru-Filho M. Physicochemical and mechanical properties of zirconium oxide and niobium oxide modified Portland cement-based experimental endodontic sealers. *Int Endod J.* 2014; 47(5):437-48.
92. Vivian RR, Zapata RO, Zeferino MA, Bramante CM, Bernardineli N, Garcia RB, et al. Evaluation of the physical and chemical properties of two commercial and three experimental root-end filling materials. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod.* 2010; 110(2):250-6.
93. Wang X, Sun H, Chang J. Characterization of $\text{Ca}_3\text{SiO}_5/\text{CaCl}_2$ composite cement for dental application. *Dent Mater.* 2008; 24(1):74-82.
94. Wang CW, Chiang TY, Chang HC, Ding SJ. Physicochemical properties and osteogenic activity of radiopaque calcium silicate-gelatin cements. *J Mater Sci Mater Med.* 2014; 25(9):2193-203.

95. Westgard JO, Barry PL, Hunt MR, Groth T. A multi-rule Shewhart chart for quality control in clinical chemistry. *Clin Chem*. 1981; 27(3):493-501.
96. Zanini M, Sautier JM, Berdal A, Simon S. Biodentine induces immortalized murine pulp cell differentiation into odontoblast-like cells and stimulates biomineralization. *J Endod*. 2012; 38(9):1220-6.
97. Zhao W, Chang J, Zhai W. Self-setting properties and in vitro bioactivity of $\text{Ca}_3\text{SiO}_5/\text{CaSO}_4 \cdot 1/2\text{H}_2\text{O}$ composite cement. *J Biomed Mater Res*. 2008; 85(2):336-44.
98. Zhou HM, Shen Y, Zheng W, Li L, Zheng YF, Haapasalo M. Physical properties of 5 root canal sealers. *J Endod*. 2013; 39(10):1281-6.