

Analysis

Operator: UEL - QUIMICA
Sample ID: LECA 28G
Sample Desc: LECA 28G
Sample weight: 0.1307 g
Outgas Time: 3.0 hrs
Analysis gas: Nitrogen
Press. Tolerance: 0.100/0.100 (ads/des)
Analysis Time: 155.9 min
Cell ID: 0

Date: 2022/11/10

Filename:

Comment:

Sample Volume: 0 cc

Outgas Temp: 300.0 C

Bath Temp: 77.3 K

Equil time: 60/60 sec (ads/des)

End of run: 2022/11/10 14:26:41

Report

Operator: UEL - QUIMICA

Date: 11/18/2022

C:\Users\236795\Documents\Odair\LECA 28G\LECA 28G.qps

Equil timeout: 240/240 sec (ads/des)

Instrument: Nova Station A

F/W version: 0.00

Area-Volume Summary

Data Reduction Parameters Data

Adsorbate	Nitrogen	Temperature	77.350K	Liquid Density:	0.808 g/cc
	Molec. Wt.:	Cross Section:	16.200 Å ²		
	28.013 g				

Surface Area Data

MultiPoint BET	2.864e+01 m ² /g
BJH method cumulative adsorption surface area	1.851e+01 m ² /g
BJH method cumulative desorption surface area	2.566e+01 m ² /g
DH method cumulative adsorption surface area	1.883e+01 m ² /g
DH method cumulative desorption surface area	2.621e+01 m ² /g

Pore Volume Data

Total pore volume for pores with Radius less than 93.31 nm at P/Po = 0.989615	7.926e-02 cc/g
BJH method cumulative adsorption pore volume	7.327e-02 cc/g
BJH method cumulative desorption pore volume	7.649e-02 cc/g
DH method cumulative adsorption pore volume	7.151e-02 cc/g
DH method cumulative desorption pore volume	7.489e-02 cc/g
HK method cumulative pore volume	1.130e-02 cc/g
SF method cumulative pore volume	1.160e-02 cc/g

Pore Size Data

Average pore Radius	5.534e+00 nm
BJH method adsorption pore Radius (Mode Dv(r))	1.542e+00 nm
BJH method desorption pore Radius (Mode Dv(r))	1.892e+00 nm
DH method adsorption pore Radius (Mode Dv(r))	1.542e+00 nm
DH method desorption pore Radius (Mode Dv(r))	1.892e+00 nm
HK method pore Radius (Mode)	1.838e-01 nm
SF method pore Radius (Mode)	2.261e-01 nm