



Effects of polyphosphates and fluoride on hydroxyapatite dissolution: A pH-stat investigation



Jackeline Gallo do Amaral^a, Alberto Carlos Botazzo Delbem^{a,*}, Juliano Pelim Pessan^a, Michele Mauricio Manarelli^a, Michele E. Barbour^b

^a Department of Pediatric Dentistry and Public Health, Araçatuba Dental School, Univ. Estadual Paulista (UNESP), Araçatuba, SP, Brazil

^b School of Oral and Dental Sciences, University of Bristol, Bristol, UK

ARTICLE INFO

Article history:

Received 27 April 2015

Received in revised form 8 November 2015

Accepted 29 November 2015

Keywords:

Erosion
Fluoride
Polyphosphates
Salivary coating
Hydroxyapatite

ABSTRACT

Objectives: This study investigated the immediate and sustained effect of sodium trimetaphosphate (TMP) and sodium hexametaphosphate (HMP) associated or not with fluoride (F) on hydroxyapatite (HA) dissolution using an erosion-like model, considering as well as the influence of salivary coating.

Design: Baseline dissolution rates were determined for HA discs using a pH-stat system. In the first set of experiments, HA discs were treated with 1100 µg F/mL, 1% or 8% of HMP, 1% or 8% of TMP and 1100 µg F/mL associated with 1% or 8% of HMP or TMP, totaling 9 groups ($n = 8$). In a second phase, HA discs were kept in pooled human saliva at 37 °C for 2 h before treatment with deionised water and 1100 µg F/mL associated with 1% or 8% of HMP or TMP, totaling 5 groups ($n = 8$). The post-treatment dissolution rate was determined from three consecutive 30-min assays. Data were analysed using 2 and 3-way ANOVA followed by Fisher and Holm–Sidak methods, respectively ($\alpha = 0.05$).

Results: All test solutions promoted reduction in HA dissolution rate when compared to baseline control in the first post-treatment run ($p < 0.001$). However, a synergistic effect was only observed between fluoride and 1% HMP. Moreover, the duration of inhibitory effect was greater when 8% HMP and 1 or 8% HMP associated with F were assessed ($p < 0.001$). The presence of salivary coating led to higher protection for all groups when compared to discs without coating ($p < 0.001$).

Conclusion: The reduction of HA dissolution rate, as well as the duration of this effect were influenced by fluoride, type and concentration of phosphate salt and the presence of a salivary coating.

© 2015 Elsevier Ltd. All rights reserved.

1. Introduction

Dental erosion has been recognized as an increasing dental problem among children, adolescents and adults (Jaeggi & Lussi, 2014). Thus, there is a growing interest in the development and evaluation of treatments which can reduce the severity and offer protection against dental erosion. In this context, fluoride (F) has been widely used as a complementary preventive measure with the aim of reducing mineral loss (Magalhães, Wiegand, Rios, Buzalaf, & Lussi, 2011). However, in order to design more effective formulations, several active ingredients other than fluorides, or in addition to, have been studied (Hooper et al., 2007; Takeshita, Castro, Sassaki, & Delbem, 2009; Takeshita, Exterkate, Delbem, &

ten Cate, 2011; Jager et al., 2013; Yamashita et al., 2013; Camara, Miyasaki, Danelon, Sassaki, & Delbem, 2014; Buzalaf, Magalhães, & Wiegand, 2014).

Promising results have led to an increasing interest in polyphosphates with and without fluoride (Moretto, Delbem, Manarelli, Pessan, & Martinhon, 2013; Moretto, Magalhães, Sassaki, Delbem, & Martinhon, 2010; Manarelli, Delbem, Lima, Castilho, & Pessan, 2013; Pancote, Manarelli, Danelon, & Delbem, 2014). Among these, sodium trimetaphosphate (TMP) and sodium hexametaphosphate (HMP) have been shown to have protective effects in both caries and erosion (Takeshita et al., 2009, 2011; Camara et al., 2014; Moretto et al., 2013, 2010; Manarelli et al., 2013; Pancote et al., 2014; Manarelli, Delbem, Lima, Castilho, & Pessan, 2014; Manarelli, Vieira, Matheus, Sassaki, & Delbem, 2011; Danelon, Takeshita, Sassaki, & Delbem, 2013; Danelon, Takeshita, Peixoto, Sassaki, & Delbem, 2014). TMP is a cyclic condensed phosphate and, according to the literature, it would preserve the stability and integrity of the enamel mineral surface during enamel erosion (Gonzalez, 1971). Sodium hexametaphosphate (HMP) is a

* Corresponding author at: Araçatuba Dental School, Univ. Estadual Paulista (UNESP), Department of Pediatric Dentistry and Public Health, Rua José Bonifácio, 1193, 16015-050 Araçatuba, SP, Brazil. Fax: +55 18 3636 3332.

E-mail addresses: adelbem@foa.unesp.br, adelbem@pq.cnpq.br (A.C.B. Delbem).

cyclic phosphate which has the ability to reduce enamel solubility (van Dijk, Borggreven, & Driessens, 1980; Andreola, Castellini, Manfredini, & Romagnoli, 2004; Castellini, Lusvardi, Malavasi, & Menabue, 2005). For both TMP and HMP, an appropriate ratio of phosphate/F should be maintained to achieve favorable effects, which seem to be related to a formation of a “barrier” on the enamel surface against mineral loss in cariogenic and erosive challenges (Camara et al., 2014; Souza, Amaral, Moraes, Sassaki, & Delbem, 2013).

Considering that the mechanisms of action of TMP and HMP are still not fully elucidated, the assessment of their effects alone or in combination with fluoride would be instructive, especially regarding the interactions of these with the tooth mineral. In this sense, a pH stat system can be used to evaluate the immediate and sustained effect of therapeutic agents on the dissolution of hydroxyapatite discs. This model has been used in previous studies (Barbour, Shellis, Parker, Allen, & Addy, 2005; Barbour, Shellis, Parker, Allen, & Addy, 2008; Jones, Rees, Shellis, & Barbour, 2013) as a model for dental tissues in studies of other inhibitors and have been shown to react to solution factors such as pH in a qualitatively similar way as enamel (Shellis, Barbour, Jones, & Addy, 2010).

Based on the above, the purpose of the present study was to evaluate the demineralisation-inhibiting properties of these phosphates alone or associated with fluoride. Considering that saliva may have a strong influence on dental erosion and on tests of anti-erosive agents (Jones et al., 2013; Buzalaf, Hannas, & Kato, 2012), the effects of TMP and HMP on dissolution of both native surfaces and of surfaces previously coated with salivary coating were assessed. The study hypothesis was that HA dissolution would be significantly reduced by the presence of fluoride, associated or not with TMP or HMP, and that this effect would be enhanced by the presence of salivary coating.

2. Material and methods

2.1. Hydroxyapatite discs and solutions preparation

Discs of compressed hydroxyapatite (HA) (mean diameter 12.7 mm and thickness 1.39 mm) were acquired from HiMed Inc., Old Bethpage, N.Y., USA. Prior to use in the pH-stat, discs were exposed to gently stirred 0.3% citric acid, pH 3.2, for 30 min at room temperature, washed in deionised water and finally air-dried to ensure consistency of response and remove loose HA particles. Before use in pH-stat, each disc was coated with nail varnish on the underside to leave a constant exposed area (126.6 mm²) available




Fig. 1. Dissolution rate of HA for the three control runs before treatment (C1–3) and after treatment (Post 1–3) with 1100 µgF/mL. Dashed line = mean control rate. *Significantly different from mean baseline control.

for reaction using an established procedure (Barbour et al., 2008). Then, discs were fixed with sticky wax to the tip of a glass tube to be inserted into the inlet port in a reproducible position.

Solutions were prepared using deionised water and reagents were acquired from Sigma–Aldrich (Poole, Dorset, UK). Solutions of citric acid were prepared at 0.3% concentrations with pH value of 3.20 (adjusted using NaOH). Fluoride (NaF; Poole, Dorset, UK) and phosphates (sodium trimetaphosphate—TMP and sodium hexametaphosphate—HMP; Poole, Dorset, UK) solutions were prepared in the following concentrations: 1100 µgF/mL, 1% and 8% of HMP or TMP and 1100 µgF/mL associated with 1% and 8% of HMP or TMP.

2.2. Measurement of dissolution rate

A pH-stat system (718 Stat Titrino; Metrohm UK, Runcorn, Cheshire, UK) with a 50-mL double-walled glass reaction vessel and a lid with 3 inlet ports was used to determine the dissolution rate of hydroxyapatite. The reaction temperature was 37 °C maintained using a water-jacketed reaction vessel and a water bath (Type GD120; Grant Instruments, Cambridge, UK). For each dissolution measurement, 30 ml of 0.3% citric acid solution was introduced into the reaction vessel and pH electrode and burette tip adapted. After the system had reached thermal equilibrium, the pH was adjusted to 3.2 by adding 1 M NaOH and then performing final fine adjustment using the pH-stat. The reaction was initiated by immersing the HA disc into the reaction vessel containing citric acid gently stirred, and the addition of titrant (50 mM HCl) was recorded for 30 min. A baseline measurement of dissolution rate was determined for each disc from the mean of three 30-min assays prior to treatment, so each disc served as its own control. Afterwards, HA discs were exposed to the chosen treatment, reattached to the glass specimen and post-treatment measurements of dissolution rate were made at 30, 60 and 90 min (totaling 3 consecutive periods of 30 min each). Fresh citric acid solutions were used for each 30-min assay.

The rate of dissolution was calculated as the slope of the linear portion from the graphic obtained of acid volume versus time (mL s⁻¹). This was converted to nmol of HA min⁻¹ mm⁻² using the area of the HA disc and a pH- and acid-dependent factor converting micromoles of acid to micromoles of hydroxyapatite (Shellis et al., 2010).

2.3. Deposition of salivary coating

Saliva was collected from two healthy volunteers participating in a saliva bank from University of Bristol. Volunteers were directed to decline the donation of saliva in the following situations: (1) they had recently taken any medication, (2) habitual smoking, (3) pregnancy or (4) if they had any upper respiratory tract infections in recent times. As required, each volunteer chewed a square of Parafilm to stimulate salivary flow and expectorated saliva into a tube until reach the 20-mL level of a polystyrene universal tube. These samples were pooled and centrifuged using a Centaur 1 (MSE, London, UK) at 4000 g for 15 min at ambient temperature. The supernatant was immediately used to treat HA specimens (2 mL/HA disc).

2.4. Treatment

2.4.1. Phase 1 (native discs)

After determining the mean baseline dissolution rate, HA discs ($n = 72$) were divided into 9 groups ($n = 8$) and treated for 2 min by immersion (with gentle stirring) in the following solutions: 1100 µgF/mL (1100); 1% or 8% HMP (1% HMP; 8% HMP); 1% or 8% TMP (1% TMP; 8% TMP); 1100 µgF/mL with 1% HMP (1100 1% HMP); 1100 µgF/mL with 8% HMP (1100 8% HMP); 1100 µgF/mL




Fig. 2. Dissolution rate of HA for the three control runs before treatment (C1–3) and after treatment (Post 1–3) with TMP and fluoride. Dashed line = mean control rate. *Significantly different from mean baseline control.

with 1% TMP (1100 1% TMP) and 1100 μg F/mL with 8% TMP (1100 8% HMP). After rinsing in deionised water, three measurements of post-treatment were performed at 30, 60 and 90 min by the same way those baseline measurements.

2.4.2. Phase 2 (saliva coated discs)

For the saliva-coated HA discs, restriction in the number of experimental groups was necessary due to the nature of the experiment regarding the saliva amount. These groups chosen were based on those that showed the best overall results in phase one. Four groups were chosen from the non-saliva-treated discs to observe the influence of salivary coating with phosphates and fluoride. A group treated with deionised water (DIW) was included as a control to observe the effect of saliva alone. Groups with phosphates that led to higher reduction of dissolution rate were selected as following: 1100 1% HMP; 1100 8% HMP; 1100 1% TMP; and 1100 8% TMP. After obtaining the control measurements of dissolution rate, discs ($n=40$) were immersed in pooled saliva supernatant for 2 h and incubated at 37 °C. After this, the discs were stored in a damp environment until the treatment with the solutions selected. HA discs were therefore treated with the selected groups by the same way for non-saliva discs. Finally, the post-treatment dissolution rate was measured on each disc at three post-treatment times, as described above.

2.5. Statistical analysis

For statistical analysis, SigmaPlot 12.0 software was used and the significance limit was set at 5%. Data from non-saliva and saliva

coated discs exhibited a normal distribution (determined using the Shapiro–Wilks test). Treatment solutions, time (baseline control, post-treatments 1–3) and presence or absence of saliva were considered as variation factors. A control value was determined for each specimen by averaging the three control runs before treatment. Then, data of groups from non-saliva coated discs were submitted to 2-way ANOVA, followed by Fisher test. When saliva was considered as variable, the 3-way ANOVA was employed and the post hoc test used was Holm–Sidak test.

3. Results

In phase 1, exposure to 1100 μg F/mL promoted a significant reduction in the dissolution rate (12%) when compared with baseline values ($p=0.041$) in the first post-treatment run. This reduction decreased beyond the first 30 min and did not persist over time (Fig. 1).

Exposure to TMP at concentrations of 1 and 8% exhibited a similar profile of dissolution rate (Fig. 2a and b) and reduced dissolution rate at 9% ($p=0.009$) and 13% ($p=0.016$), respectively, in the first post treatment run. This reduction persisted over time for the 8%TMP, presenting 10% of reduction in the third post-treatment run ($p=0.048$). When either 1 or 8% TMP concentrations were associated to fluoride (1100 μg F/mL), a significant reduction in HA dissolution was seen for 1100 8% TMP over time, being 22% lower than the baseline values ($p<0.001$) in the first post-treatment run and 8% ($p=0.048$) in the third post-treatment run (Fig. 2c and d). The maximum reduction of dissolution rate in this study was observed for HMP. When 1 and 8% of HMP were




Fig. 3. Dissolution rate of HA for the three control runs before treatment (C1-3) and after treatment (Post 1-3) with HMP and fluoride. Dashed line = mean control rate. *Significantly different from mean baseline control.




Fig. 4. Graphic representation of HA dissolution rate reduction according to the treatments, and post-treatment run. a = post-treatment 1 (30 min), b = post-treatment 2 (60 min) and c = post-treatment 3 (90 min). Bars indicate the standard deviation of the mean. Different lowercase letters represent statistical difference among the groups (Fisher's test, $p < 0.001$). *Indicate significant difference from mean baseline control.




Fig. 5. Graphic representation of HA dissolution rate reduction according to the treatments, saliva and post-treatment run. a = post-treatment 1 (30 min), b = post-treatment 2 (60 min) and c = post-treatment 3 (90 min). Bars indicate the standard deviation of the mean. Distinct capital letters represent statistical difference among the groups without salivary coating. Different lowercase letters represent statistical difference among the groups with salivary coating (Holm–Sidak, $p < 0.001$).

assessed, the reduction of dissolution rate was, respectively, 24% ($p < 0.001$) and 61% ($p < 0.001$) at the first post-treatment run, 17% ($p = 0.004$) and 41% ($p < 0.001$) at the second post-treatment run, and 4% ($p = 0.374$) and 40% ($p < 0.001$) at the third post-treatment, showing a significant reduction of dissolution rate versus baseline over time for HMP at 8% (Fig. 3a and b). For the 1100 1% HMP and 1100 8% HMP, the reduction rates were very similar, but persisted higher for the 1100 8% HMP in the second post-treatment ($p < 0.001$) (Fig. 3c and d). A comparison among groups can be observed in Fig. 4.

Fig. 5 shows the results from the saliva coated discs regarding the percentage reduction in the dissolution rate. There was a significant reduction of dissolution rate ($p < 0.001$) for all groups evaluated in the presence of salivary coating, when compared with their treatment with DIW or with their counterparts not covered by salivary coating. Also, the presence salivary coating alone resulted in a significant reduction of the hydroxyapatite dissolution rate compared to the baseline rate ($p < 0.001$), as seen for discs treated with DIW. The higher reduction of dissolution rate and persistence of effect over time in the presence of saliva was observed when HMP (1 and 8%) was associated with fluoride. There was a higher persistence of effect over time for the 1100 associated with 8% HMP ($p < 0.001$).

4. Discussion

TMP and HMP associated with fluoride have been shown effective against both dental caries and erosion (Takeshita et al., 2009, 2011; Camara et al., 2014; Moretto et al., 2013, 2010; Manarelli et al., 2013, 2014, 2011; Pancote et al., 2014; Danelon et al., 2013, 2014). As pH-stat method has been used successfully as

a technique to study dental erosion, providing information about interactions with hydroxyapatite and the persistence of the inhibitory effect during repeated erosive challenges, in this study this method was employed to investigate the effect of these phosphates with or without fluoride.

In the present study, both phosphate salts evaluated inhibited dissolution of HA by different concentrations. The reduction of dissolution rate of HA treated with fluoride did not persist significantly further than the first post-treatment run, which is in agreement with Jones et al. (2013). Although the fluoride concentration used in the present study was higher (1100 $\mu\text{gF/mL}$) than that used by Jones et al. (2013) (300 $\mu\text{gF/mL}$), no additional effect on HA dissolution was observed. The protective effect of fluoride against dental erosion is probably given by a formation of a protective layer that containing calcium fluoride (CaF_2) (Magalhães et al., 2011), and the adsorbed fluoride could be reduced by the acid challenge over time (Jones et al., 2013).

Regarding the polyphosphates evaluated, higher inhibitory effect was found when compared with 1100, especially for HMP. For TMP alone, a similar dissolution profile was observed for both concentrations evaluated, showing a sustained inhibition over time for the 8% TMP. When TMP was associated with fluoride, a higher immediate and a sustained effect for the 1100 8% TMP was observed (Fig. 2a and b). Based on the current results (Pancote et al., 2014; Manarelli et al., 2014) and on previous studies, it becomes clear that an appropriate F/TMP ratio can reduce enamel demineralisation as well as the mineral loss in erosive challenges. Such effects, however, are not associated with formation of high amounts of CaF_2 , as described for fluoride. This effect seems to be related to a formation of a “barrier” of TMP on the enamel surface, which limits the diffusion of acid into the enamel as well as the

deposition of CaF_2 on this barrier, and the retention of ions (Ca^{++} and CaF^+) in the TMP molecule, which would be released during pH challenges (Pancote et al., 2014; Cochrane, Saranathan, Cai, Cross, & Reynolds, 2008). TMP in the absence of fluoride has shown a little or no action on dental enamel (Takeshita et al., 2009).

As has been stated for TMP, HMP has been shown to provide a less soluble hydroxyapatite as well as reduce the ion diffusion into the enamel (van Dijk et al., 1980). Camara et al. (2014) suggested that HMP is capable of binding to surface enamel and remain bound and also demonstrated that, in the absence of fluoride, a significant reduction of mineral loss was observed 0.5% HMP was used, when compared to placebo, suggesting that HMP (negatively charged) can adsorb at the positive sites of enamel surfaces forming a “coat” after treatment that acts as a protective layer on the enamel. In the present study a higher reduction of dissolution rate was found for the 8% HMP concentration (with or without fluoride), which differ that data found by Camara et al. (2014) that showed higher mineral loss with increased HMP concentration in association with fluoride (250 $\mu\text{g F/mL}$) in an in vitro caries model. In the present study HA dissolution was assessed using an erosion-like model with a different F concentration, which might have influenced in the different results obtained. Regarding HMP and TMP structure, these salts have six and three phosphate groups, respectively, what might help explain the greater results obtained with HMP; when in the oral environment, HMP could form a stronger “barrier” on enamel surface and provide a higher amount of binding sites for the retention of ions (Ca^{++} and CaF^+) in comparison with TMP.

Considering the influence of saliva on the effect of anti-erosive agents, the presence of a salivary coating was considered in the second set of experiments. An exposure time of 2 h to saliva ensured an effect on HA discs and allowed to investigate the interactions with polyphosphates in this study. According to literature a significant effect can be obtained for exposure times ≥ 60 min (Jones et al., 2013; Wetton, Hughes, West, & Addy, 2006). As expected, the formation of a salivary coating resulted in a significant reduction of the hydroxyapatite dissolution rate (33%), which is in line with a previous study conducted with the same methods of analysis (Jones et al., 2013), showing a reduction in HA dissolution of 41%. Furthermore, the presence of salivary coating led to higher protection for all groups when compared to discs without the pellicle (Fig. 5). The profile obtained was similar to those obtained for native discs; however all tested solutions with fluoride and associated to HMP or TMP promoted an additional effect in the presence of saliva and polyphosphates. Nonetheless this effect (immediate and sustained) was greater for the solutions containing HMP, showing that the salivary coating did not reduce or hinder the polyphosphates action.

To conclude, confirming this study hypothesis, the reduction of HA dissolution rate as well as the duration of this effect was influenced by fluoride, type and concentration of phosphate salt, and further enhanced by the presence of a salivary coating. This is important from a clinical point of view, since the tooth surfaces in vivo are coated with salivary pellicle under normal conditions.

Conflict of interests

None of the authors had a financial or personal conflict of interest in relation to this study.

Funding

The first author received a PhD scholarship (process BEX 9221-12-3) from CAPES Foundation, Ministry of Education of Brazil.

Ethical approval

Human saliva was obtained from a saliva bank from the University of Bristol, following the ethical guidelines of the institution.

Acknowledgements

The authors thank the CAPES for the Ph.D. scholarship (process BEX 9221-12-3) for the first author.

References

- Andreola, F., Castellini, E., Manfredini, T., & Romagnoli, M. (2004). The role of sodium hexametaphosphate in the dissolution process of kaolinite and kaolin. *Journal of the European Ceramic Society*, 24(7), 2113–2124.
- Barbour, M. E., Shellis, R. P., Parker, D. M., Allen, G. C., & Addy, M. (2005). An investigation of some food-approved polymers as agents to inhibit hydroxyapatite dissolution. *European Journal of Oral Sciences*, 113(6), 457–461.
- Barbour, M. E., Shellis, R. P., Parker, D. M., Allen, G. C., & Addy, M. (2008). Inhibition of hydroxyapatite dissolution by whole casein: the effects of pH, protein concentration, calcium, and ionic strength. *European Journal of Oral Sciences*, 116(5), 473–478.
- Buzalaf, M. A., Hannas, A. R., & Kato, M. T. (2012). Saliva and dental erosion. *Journal of Applied Oral Science*, 20(5), 493–502.
- Buzalaf, M. A., Magalhães, A. C., & Wiegand, A. (2014). Alternatives to fluoride in the prevention and treatment of dental erosion. *Monographs in Oral Science*, 25, 244–252.
- Camara, D. M., Miyasaka, M. L., Danelon, M., Sassaki, K. T., & Delbem, A. C. (2014). Effect of low-fluoride toothpastes combined with hexametaphosphate on in vitro enamel remineralization. *Journal of Dentistry*, 42(3), 256–262.
- Castellini, E., Lusvardi, G., Malavasi, G., & Menabue, L. (2005). Thermodynamic aspects of the adsorption of hexametaphosphate on kaolinite. *Journal of Colloid and Interface Science*, 292(2), 322–329.
- Cochrane, N. J., Saranathan, S., Cai, F., Cross, K. J., & Reynolds, E. C. (2008). Enamel subsurface lesion remineralization with casein phosphopeptide stabilized solutions of calcium, phosphate and fluoride. *Caries Research*, 42(2), 88–97.
- Danelon, M., Takeshita, E. M., Sassaki, K. T., & Delbem, A. C. B. (2013). In situ evaluation of a low fluoride concentration gel with sodium trimetaphosphate in enamel re-mineralization. *American Journal of Dentistry*, 26(1), 15–20.
- Danelon, M., Takeshita, E. M., Peixoto, L. C., Sassaki, K. T., & Delbem, A. C. (2014). Effect of fluoride gels supplemented with sodium trimetaphosphate in reducing demineralization. *Clinical Oral Investigations*, 18(4), 1119–1127.
- Gonzalez, M. (1971). Effect of trimetaphosphate ions on the process of mineralization. *Journal of Dental Research*, 50(5), 1056–1064.
- Hooper, S. M., Newcombe, R. G., Faller, R., Eversole, S., Addy, M., & West, N. X. (2007). The protective effects of toothpaste against erosion by orange juice: studies in situ and in vitro. *Journal of Dentistry*, 35(6), 476–481.
- Jaeggi, T., & Lussi, A. (2014). Prevalence, incidence and distribution of erosion. *Monographs in Oral Science*, 25, 55–73.
- Jager, D. H., Vissink, A., Timmer, C. J., Bronkhorst, E., Vieira, A. M., & Huysmans, M. C. (2013). Reduction of erosion by protein-containing toothpastes. *Caries Research*, 47(2), 135–140.
- Jones, S. B., Rees, G. D., Shellis, R. P., & Barbour, M. E. (2013). The effect of monoalkyl phosphates and fluoride on dissolution of hydroxyapatite, and interactions with saliva. *Caries Research*, 47(5), 355–363.
- Magalhães, A. C., Wiegand, A., Rios, D., Buzalaf, M. A., & Lussi, A. (2011). Fluoride in dental erosion. *Monographs in Oral Science*, 22, 158–170.
- Manarelli, M. M., Vieira, A. E., Matheus, A. A., Sassaki, K. T., & Delbem, A. C. (2011). Effect of mouth rinses with fluorides and trimetaphosphate on enamel erosion: an in vitro study. *Caries Research*, 45(6), 506–509.
- Manarelli, M. M., Delbem, A. C. B., Lima, T. M. T., Castilho, F. C. N., & Pessan, J. P. (2013). Effect of fluoride varnish supplemented with sodium trimetaphosphate on enamel erosion and abrasion. *American Journal of Dentistry*, 26(6), 307–312.
- Manarelli, M. M., Delbem, A. C., Lima, T. M., Castilho, F. C., & Pessan, J. P. (2014). In vitro remineralizing effect of fluoride varnishes containing sodium trimetaphosphate. *Caries Research*, 48(4), 299–305.
- Moretto, M. J., Magalhães, A. C., Sassaki, K. T., Delbem, A. C., & Martinhon, C. C. R. (2010). Effect of different fluoride concentrations of experimental dentifrices on enamel erosion and abrasion. *Caries Research*, 44(2), 135–140.
- Moretto, M. J., Delbem, A. C., Manarelli, M. M., Pessan, J. P., & Martinhon, C. C. (2013). Effect of fluoride varnish supplemented with sodium trimetaphosphate on enamel erosion and abrasion: an in situ/ex vivo study. *Journal of Dentistry*, 41(12), 1302–1306.
- Pancote, L. P., Manarelli, M. M., Danelon, M., & Delbem, A. C. B. (2014). Effect of fluoride gels supplemented with sodium trimetaphosphate on enamel erosion and abrasion: in vitro study. *Archives of Oral Biology*, 59(3), 336–340.
- Shellis, R. P., Barbour, M. E., Jones, S. B., & Addy, M. (2010). Effects of pH and acid concentration on erosive dissolution of enamel, dentine, and compressed hydroxyapatite. *European Journal of Oral Sciences*, 118(5), 475–482.

- Souza, J. A., Amaral, J. G., Moraes, J. C., Sassaki, K. T., & Delbem, A. C. (2013). Effect of sodium trimetaphosphate on hydroxyapatite solubility: an in vitro study. *Brazilian Dental Journal*, 24(3), 235–240.
- Takeshita, E. M., Castro, L. P., Sassaki, K. T., & Delbem, A. C. B. (2009). In vitro evaluation with low fluoride content supplemented with trimetaphosphate. *Caries Research*, 43(1), 50–56.
- Takeshita, E. M., Exterkate, R. A., Delbem, A. C., & ten Cate, J. M. (2011). Evaluation of different fluoride concentrations supplemented with trimetaphosphate on enamel de- and remineralization in vitro. *Caries Research*, 45(5), 494–497.
- Wetton, S., Hughes, J., West, N., & Addy, M. (2006). Exposure time of enamel and dentine to saliva for protection against erosion: a study in vitro. *Caries Research*, 40(30), 213–217.
- Yamashita, J. M., Torres, N. M., Moura-Grec, P. G., Marsicano, J. A., Sales-Peres, A., & Sales-Peres, S. H. (2013). Role of arginine and fluoride in the prevention of eroded enamel: an in vitro model. *Australian Dental Journal*, 58(4), 478–482.
- van Dijk, J. W., Borggreven, J. M., & Driessens, F. C. (1980). The effect of some phosphates and a phosphonate on the electrochemical properties of bovine enamel. *Archives of Oral Biology*, 25(8–9), 591–595.